

SUN PROTECTION

OFFICE 1012

Number	Colour	89	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			127	2300	3000	R	T	A	R	T	A			
1000	white	✓	✓	✓	✓	92%	5%	3%	78%	11%	11%	6-7	0,31	0,43
2025	beige	✓	✓	✓	✓	90%	6%	4%	78%	7%	15%	6-7	0,32	0,43
2378	linen	✓	✓	✓	-	83%	7%	10%	78%	6%	16%	6-7	0,31	0,44
327	grise	✓	✓	✓	✓	85%	4%	11%	78%	6%	16%	6-7	0,31	0,42
2011	dune	✓	✓	✓	✓	85%	5%	10%	78%	7%	15%	6-7	0,32	0,42
2353	safari	✓	✓	✓	✓	86%	5%	9%	76%	8%	16%	6-7	0,32	0,43
9058	anthracite	✓	✓	✓	✓	84%	2%	14%	76%	3%	21%	6-7	0,32	0,44
2272	sand	✓	✓	✓	-	86%	3%	11%	76%	7%	17%	6-7	0,31	0,42
2323	lava sand	✓	✓	✓	-	86%	5%	9%	79%	6%	15%	6-7	0,32	0,43
9164	graphite	✓	✓	✓	✓	83%	1%	16%	74%	3%	23%	6-7	0,33	0,43
6017	sun	✓	✓	✓	-	84%	8%	8%	77%	12%	11%	6-7	0,31	0,44
2327	moon rock	✓	✓	✓	-	82%	2%	16%	75%	5%	20%	6-7	0,33	0,44
5188	ink blue	✓	✓	✓	✓	87%	1%	12%	79%	2%	19%	6-7	0,30	0,43
4037	lime	✓	✓	✓	-	83%	5%	12%	76%	8%	16%	6-7	0,32	0,44
5024	blue	✓	✓	✓	-	85%	1%	14%	76%	7%	17%	6-7	0,32	0,43

All printed colours and textures only provide orientation and are not reference pattern.

Usable for
Colour Range
Composition
Width
Cutting Process
Processing Direction

Roller / Vertical / Panel Track
15
100 % PES
89 / 127 / 2300 / 3000 mm
cold
warp & weft

Weight
Thickness
Moisture proofed
PVC free
OekoTex

320 g/m2
0,40 mm
yes
yes
yes



Flame
retardant


DIN 4102, B1
BS 5867 part 2



Perlex



suitable for
workstations



C
dim out



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.