

DARK Project

Number	Colour	89	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			127	2300	3000	R	T	A	R	T	A			
1000	white-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2304	ivory-white	✓	✓	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9030	light grey-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9124	light grey-white	✓	✓	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2025	beige-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9060	mouse grey-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9263	silver-grey-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2272	sand-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9162	dark grey-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9037	manhattan-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2445	beach-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9092	anthracite-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
6025	yellow-white	✓	✓	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
4125	light green-white	✓	✓	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
5053	blue-white	✓	✓	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58

All printed colours and textures only provide orientation and are not reference pattern.

Usable for
Colour Range
Composition
Width
Cutting Process
Processing Direction

Roller / Vertical / Panel Track
15
100 % PES
89 / 127 / 2300 / 3000 mm
cold
warp & weft

Weight
Thickness
Moisture proofed
PVC free
OekoTex

420 g/m²
0,50 mm
yes
yes
yes




Flame
retardant

DIN 4102, B1
NF P 92-503-507,M1
BS 5867 part 2
UNI 8456-UNI 9174 C1
EN 13773 class 1
NFPA 701- USA



suitable for
workstations



D
black-out



Standard 100
by Oeko-Tex[®]

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.